

1. PRODUCT NAME

Belzona® 1111 (Super Metal)
Engineering grade repair system for repairing and rebuilding machinery and equipment.

Also used as a high strength structural adhesive for bonding or for creation of irregular load bearing shims with good electrical insulation characteristics.

For use in Original Equipment Manufacture or repair situations.

2. MANUFACTURER

Belzona Inc.,
2000 N.W. 88th Court
Miami, Florida 33172

Belzona Polymerics Ltd.
Claro Road, Harrogate,
HG1 4DS, England.

3. PRODUCT DESCRIPTION

A two component paste grade system based on a silicon steel alloy blended with high molecular weight reactive polymers and oligomers. When cured, the material is durable yet fully machinable.

Applications

- Shafts
- Hydraulic rams
- Bearing housings
- Keyways
- Engine blocks
- Casings
- Pipes
- Tanks
- Flange faces

4. TECHNICAL DATA

Base Component

Appearance	Paste
Color	Dark gray
Gel strength at 77°F (25°C)	>150 g/cm HF
Density	2.70 - 2.90 g/cm ³

Solidifier Component

Appearance	Paste
Color	Light gray
Gel strength at 77°F (25°C)	>70 g/cm QV
Density	1.63 - 1.69 g/cm ³

Mixed Properties at 68°F (20°C)

Mixing Ratio by Weight (Base : Solidifier)	5 : 1
Mixing Ratio by Volume (Base : Solidifier)	3 : 1
Mixed Form	Paste
Peak Exotherm Temperature	239 - 284°F (115 - 140°C)
Time to Peak Exotherm	25 - 42 mins.
Slump Resistance	nil at 0.5 inch 1.27 cm)
Mixed Density	2.5 g/cm ³

• Shelf Life:

Separate base and solidifier components shall have a shelf life of at least 5 years when stored between 32°F (0°C) and 86°F (30°C).

• Working Life:

Will vary according to temperature. At 77°F (25°C) the usable life of mixed material is 15 minutes.

• Volume Capacity:

The volume capacity of a 1 kg. unit of mixed **Belzona® 1111** is 24.3 in³ (398 cm³).

• Cure Time:

Will be reduced for thicker sections and extended for thinner applications. At a thickness of approximately ¼ in. (6 mm), allow to solidify for the times shown in the chart below before subjecting it to the conditions indicated.

5. PHYSICAL/MECHANICAL PROPERTIES

Determined after 7 days cure at 77°F (25°C). Post curing the material with heat results in a more highly cross-linked polymer.

For enhanced performance this material may be post-cured by heating to 212°F (100°C) for a period of up to 24 hours.

• Abrasion Resistance:

Taber
The Taber abrasion resistance with 1 kg load is typically:
H10 Wheels (Wet) 889 mm³
CS17 Wheels (Dry) 56 mm³
loss per 1000 cycles

• Adhesion:

Cleavage
When tested to ASTM D1062 typical values will be:
Mild steel 1400 lbs./in. (25 kg/mm)

Tensile Shear

When tested in accordance with ASTM D1002, using degreased strips, grit blasted to a 3-4 mil profile, typical values will be:

Aluminum	1,800 psi (126 kg/cm ²)
Brass	1,670 psi (117 kg/cm ²)
Copper	1,900 psi (133 kg/cm ²)
Formica	>500 psi (35 kg/cm ²)*
Mild steel	2,700 psi (190 kg/cm ²)
Polyester/ glass fiber	>700 psi (49 kg/cm ²)*
Stainless steel	2,800 psi (197 kg/cm ²)

* *breakdown of substrate*

• Chemical Resistance:

Once fully cured, the material will demonstrate excellent resistance to the following chemicals;

- carbonic acid
- 10% hydrochloric acid
- 10% nitric acid
- 5% phosphoric acid
- 10% sulfuric acid
- 20% ammonia solution
- lime water
- 20% potassium hydroxide
- 20% sodium hydroxide
- propanol
- butanol
- ethylene glycol
- diethanolamine
- methylamine (25% in water)
- hydrocarbons
- mineral oils
- inorganic salts

* For a more detailed description of chemical resistance properties, refer to Product Data M503.

CURE TIMES

TEMPERATURE	41°F (5°C)	50°F (10°C)	59°F (15°C)	68°F (20°C)	77°F (25°C)	86°F (30°C)
Movement or use involving no loading or immersion	4 hrs	3 hrs	2¼ hrs	1¾ hrs	1 hr	¾ hr
Machining and/or light loading	6 hrs	4 hrs	3 hrs	2 hrs	1½ hrs	1 hr
Full electrical, mechanical or thermal loading	4 days	2 days	1½ day	1 day	20 hrs	16 hrs
Immersion in chemicals	5 days	4 days	3 days	2 days	1½ days	1 day

• **Compressive Strength:**

When tested in accordance with ASTM D695, typical values obtained will be:
13,000 psi (914 kg/cm²) ambient cure
15,000 psi (1055 kg/cm²) post cure

• **Compressive Modulus:**

When tested in accordance with ASTM D695, typical values obtained will be:
ambient cure 2.7 x 10⁵ psi
(1.9 x 10⁴ kg/cm²)
post cure 3.7 x 10⁵ psi
(2.6 x 10⁴ kg/cm²)

• **Corrosion Resistance:**

Will show no visible signs of corrosion after 5,000 hours exposure in the ASTM B117 salt spray cabinet.

• **Electrical Properties:**

Dielectric Strength

Tested to ASTM D149 is typically 84 volts/mil (3360 volts/mm)

Dielectric Constant

Tested to ASTM D150 is typically 10 at 1000Hz
6 at 1 MHz

Dissipation Factor

Tested to ASTM D150 is typically <0.0005 at 1 MHz
0.0120 at 1000 HZ

Volume Resistivity

Tested to ASTM D257 is typically 5.3 x 10¹² ohm cm.

Surface Resistivity

Tested to ASTM D257 is typically 4.7 x 10¹³ ohm.

• **Elongation:**

When determined in accordance with ASTM D638, typical values will be:
0.277% ambient cure
0.325% post cure

• **Flexural Strength:**

When tested to ASTM D790, typical values obtained will be:
9,000 psi (633 kg/cm²) ambient cure
13,000 psi (914 kg/cm²) post cure

• **Flexural Modulus:**

When tested in accordance with ASTM D790, typical values obtained will be:
ambient cure 10.6 x 10⁵ psi
(7.45 x 10⁴ kg/cm²)
post cure 9.1 x 10⁵ psi
(6.4 x 10⁴ kg/cm²)

• **Hardness:**

The hardness of the material when tested to ASTM D2240 is typically 89 Shore D.

• **Heat Distortion Temperature:**

Tested to ASTM D648 (264 psi fiber stress), typical values obtained will be:
136°F (58°C) ambient cure
216°F (102°C) post cure

• **Heat Resistance:**

For many typical applications, the product is thermally stable up to 392°F (200°C) dry and 200°F (93°C) wet, and down to -40°F (-40°C)

• **Impact Strength:**

The impact strength when tested to ASTM D256 is typically:
1.3 ft.lb./in., 70 J/m (un-notched) or
0.65 ft.lb./in., 35 J/m (reverse notched)

• **Shrinkage:**

Shrinkage is typically <0.025% when tested in accordance with DOD-C-24176A method 4.6.12.

• **Tensile Strength:**

When determined in accordance with ASTM D638, typical values will be:
3535 psi (24.37 MPa) ambient cure
4236 psi (29.21 MPa) post cure

• **Young's Modulus:**

When determined in accordance with ASTM D638, typical values will be:
1.34x10⁶ psi (9252 MPa) ambient cure
2.03x10⁶ psi (13992 MPa) post cure

• **Thermal Expansion:**

Tested to ASTM E228 the coefficient of thermal expansion is typically 31.7 ppm/°C.

6. SURFACE PREPARATION AND APPLICATION PROCEDURES

For proper technique, refer to the Belzona® Instructions For Use leaflet which is enclosed with each packaged product.

7. AVAILABILITY AND COST

Belzona® 1111 is available from a network of Belzona® Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona® Distributor in your area.

8. WARRANTY

Belzona® guarantees this product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona® Instructions For Use leaflet. Belzona® further guarantees that all its products are carefully manufactured to ensure the highest quality possible and tested strictly in accordance with universally recognised standards (ASTM, ANSI, BS, DIN, etc.). Since Belzona® has no control over the use of the product described herein, no warranty for any application can be given.

9. TECHNICAL SERVICES

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

10. HEALTH AND SAFETY

Prior to using this material, please consult the relevant Material Safety Data Sheets.

11. APPROVALS/ ACCEPTANCES

The material has received recognition from organizations worldwide including:
AMERICAN BUREAU OF SHIPPING
U.S. DEPARTMENT OF NAVY
GAZ DE FRANCE
RJB MINING
AIR B.P.
NATO
NUCLEAR INDUSTRY (DBA TESTED)
U.S.D.A.
GENERAL MOTORS
TOYOTA
NIPPON KAIJI KYOKAI
RUSSIAN REGISTER OF SHIPPING
POLISH REGISTER OF SHIPPING
KOREAN REGISTER OF SHIPPING
CHINA CLASSIFICATION SOCIETY
BUREAU VERITAS

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2012 Belzona International Limited. Belzona® is a registered trademark.



ISO 9001:2008
Q 09335
ISO 14001:2004
EMS 509612

Manufactured under an ISO 9000
Registered Quality Management System

